

DMH 333 EPDM FDA Ethylene propylene diene rubber

Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit	
colour				black	black	
hardness	23°C/3 sec.	ISO 868	Shore A	85 ± 5	85 ± 5	
hardness	23°/15 sec.	ISO 868	Shore A	84 ± 5	84 ± 5	
modulus 100%	23°C	DIN 53 504	MPa		psi	
tensile strength	23°C	DIN 53 504	MPa	≥ 10	psi	≥ 1450
elongation at break	23°C	DIN 53 504	%	≥ 100	%	≥ 100
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 4	lbf/inch	≥ 23
spec. gravity	23°C	ISO 1183	kg/m ³	1180	g/cm ³	1,18
rebound elasticity	23°C	DIN 53 512	%	40	%	40
abrasion	23°C	DIN 53 516	mm ³	160	mm ³	160
compression set	*	ISO 815	%	≤ 10	%	≤ 10
compression set	**	ISO 815	%	≤ 10	%	≤ 10
compression set	***	ISO 815	%		%	
minimum service temperature			°C	-45	°F	-49
maximum service temperature			°C	130	°F	266
temp. max water/steam			°C	130	°F	266
temp. max hot air			°C	150	°F	302

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on ethylene, propylene and diene

Resistant to: (hot) water, acids, bases, ketones, HFC- and HFD-fluids, lyes, brake fluids based on polyglycols

Not resistant to: aliphatic, aromatic and chlorinated hydrocarbons, greases, fuels

Foodstuff approval: FDA compliant, 1935/2004 EC

Maximum recommended service temperature (FDA applications): 90°C

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 10-2020

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11

T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500

E: office@dmh.at  www.dmh.at

