

DMH 341 MVQ FDA Vinyl methyl silicone rubber Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit
colour				translucent	translucent
hardness	23°C/3 sec.	ISO 868	Shore A	85 ± 5	85 ± 5
hardness	23°C/15 sec.	ISO 868	Shore A	85 ± 5	85 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 4	≥ 580
tensile strength	23°C	DIN 53 504	MPa	≥ 7	≥ 1015
elongation at break	23°C	DIN 53 504	%	≥ 210	≥ 210
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 8	≥ 45
spec. gravity	23°C	ISO 1183	kg/m ³	1225	1,22
rebound elasticity	23°C	DIN 53 512	%	38	38
abrasion	23°C	DIN 53 516	mm ³		
compression set	*	ISO 815	%	≤ 14	≤ 14
compression set	**	ISO 815	%	≤ 22	≤ 22
compression set	***	ISO 815	%		
minimum service temperature			°C	-60	-76
maximum service temperature			°C	200	392
temp. max water/steam			°C	110	230
temp. max hot air, short			°C	300	572

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 175°C 25% def.

Chemical Properties

Copolymer, based on methyl, vinyl and silicone

Resistant to: hot air, ozone, hot water and acetic acid

Not resistant to: aliphatic and aromatic hydrocarbons and esters

Foodstuff approval: FDA compliant in it's active substances to § 177.2600, CFR 21

" Rubber Articles Intended for Repeated Use "

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 04-2020

DMH

SOLUTION FOR SEALS

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11
T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500
E: office@dmh.at  www.dmh.at

