

## DMH 352 FPM/Viton black Fluoro Rubber

### Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit	unit
colour				black		black
hardness	23°C/3 sec.	ISO 868	Shore A	85 ± 5	Shore A	85 ± 5
hardness	23°C/15 sec.	ISO 868	Shore A	83 ± 5	Shore A	83 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 7	psi	≥ 1015
tensile strength	23°C	DIN 53 504	MPa	≥ 9	psi	≥ 1305
elongation at break	23°C	DIN 53 504	%	≥ 130	%	≥ 130
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 7	lbf/inch	≥ 39
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	1870	g/cm <sup>3</sup>	1,87
rebound elasticity	23°C	DIN 53 512	%	9	%	9
abrasion	23°C	DIN 53 516	mm <sup>3</sup>		mm <sup>3</sup>	
compression set	*	ISO 815	%	≤ 13	%	≤ 13
compression set	**	ISO 815	%	≤ 15	%	≤ 15
compression set	***	ISO 815	%	≤	%	≤
minimum service temperature			°C	-20	°F	-4
maximum service temperature			°C	210	°F	410
temp. max water/steam			°C		°F	
temp. max hot air			°C	280 short	°F	536 short

\* 24h 70°C 25% def.

\*\* 24h 100°C 25% def.

\*\*\* 24h 175°C 25% def.

### Chemical Properties

Copolymer, based on fluoro

Resistant to: fats, crude oil, mineral oil, gasoline, aliphatic and aromatic hydrocarbons

Not resistant to: glycols, ketones, most fluids containing amines, water/steam

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 04-2020