

DMH 151 LT-PU+ Mechanical, Physical and Thermal Properties

thermoplastic polyurethane with resistance to hydrolysis

properties	condition	standard	unit	unit	unit	
colour				blue	blue	
hardness	23°C	ISO 868	Shore A	94 ± 2	Shore A	94 ± 2
hardness	23°C/3 sec.	ISO 868	Shore D	49 ± 3	Shore D	49 ± 3
hardness	23°C/15 sec.	ISO 868	Shore D	48 ± 3	Shore D	48 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 12	psi	≥ 1740
modulus 300 %	23°C	DIN 53 504	MPa	≥ 22	psi	≥ 3190
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6525
elongation at break	23°C	DIN 53 504	%	≥ 400	%	≥ 400
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 80	lbf/inch	≥ 450
spec. gravity	23°C	ISO 1183	kg/m ³	1110	g/cm ³	1,11
abrasion	23°C	DIN 53 516	mm ³	20	mm ³	20
compression set	*	ISO 815	%	≤ 30	%	≤ 30
compression set	**	ISO 815	%	≤ 35	%	≤ 35
minimum service temperature			°C	-55	°F	-67
maximum service temperature			°C	110	°F	230

* 24h 70°C 25% def.

** 24h 100°C 25% def.

Chemical Properties

Copolymer, based on aromatic isocyanate and diols

Resistant to oil, water, ozone, microbes

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 04-2020

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11

T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500

E: office@dmh.at  www.dmh.at

