

## DMH 170 SL-PU casted thermoplastic polyurethane with solid lubricant

### Mechanical, Physical and Thermal Properties

| properties                  | condition    | standard     | unit              | unit   | unit                   |
|-----------------------------|--------------|--------------|-------------------|--------|------------------------|
| colour                      |              |              |                   | grey   | grey                   |
| hardness                    | 23°C         | ISO 868      | Shore A           | 96 ± 2 | Shore A 96 ± 2         |
| hardness                    | 23°C/3 sec.  | ISO 868      | Shore D           | 48 ± 3 | Shore D 48 ± 3         |
| hardness                    | 23°C/15 sec. | ISO 868      | Shore D           | 45 ± 3 | Shore D 45 ± 3         |
| modulus 100%                | 23°C         | DIN 53 504   | MPa               | ≥ 12   | psi ≥ 1740             |
| modulus 300 %               | 23°C         | DIN 53 504   | MPa               | ≥ 22   | psi ≥ 3190             |
| tensile strength            | 23°C         | DIN 53 504   | MPa               | ≥ 45   | psi ≥ 6525             |
| elongation at break         | 23°C         | DIN 53 504   | %                 | ≥ 350  | % ≥ 350                |
| tear strength               | 23°C         | DIN ISO 34-1 | kN/m              | ≥ 80   | lbf/inch ≥ 450         |
| spec. gravity               | 23°C         | ISO 1183     | kg/m <sup>3</sup> | 1190   | g/cm <sup>3</sup> 1,19 |
| abrasion                    | 23°C         | DIN 53 516   | mm <sup>3</sup>   | 15     | mm <sup>3</sup> 15     |
| compression set             | *            | ISO 815      | %                 | ≤ 30   | % ≤ 30                 |
| compression set             | **           | ISO 815      | %                 | ≤ 35   | % ≤ 35                 |
| minimum service temperature |              |              | °C                | -20    | °F -4                  |
| maximum service temperature |              |              | °C                | 110    | °F 230                 |

\* 24h 70°C 25% def.

\*\* 24h 100°C 25% def.

### Chemical Properties

Copolymer, based on aromatic isocyanate and diols and internal lubricants

Resistant to oil, hot water, hot air, ozone

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 04-2020