

DMH 171 SL-PU 55D casted thermoplastic polyurethane with resistance to hydrolysis (TPU) and solid lubricant

Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit	unit
colour				dark grey		dark grey
hardness	23°C/3 sec.	ISO 868	shore D	55 ± 3	shore D	55 ± 3
hardness	23°C/15 sec.	ISO 868	shore D	49 ± 3	shore D	49 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 16	psi	≥ 2321
modulus 300 %	23°C	DIN 53 504	MPa	≥ 35	psi	≥ 5076
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6526
elongation at break	23°C	DIN 53 504	%	≥ 330	%	≥ 330
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 110	lbf/inch	≥ 630
spec. gravity	23°C	ISO 1183	kg/m ³	1210	g/cm ³	1,21
abrasion	23°C	DIN 53 516	mm ³	25	mm ³	25
compression set	*	ISO 815	%	≤ 30	%	≤ 30
compression set	**	ISO 815	%	≤ 35	%	≤ 35
minimum service temperature			°C	-20	°F	-22
maximum service temperature			°C	110	°F	240

* 24h 70°C 20% def.

** 24h 100°C 20% def.

Chemical Properties

Copolymer, based on aromatic isocyanate and diols and internal lubricants

Resistant to oil, petrol, hot water, hot air, ozone

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 04-2020